AMENDMENT NO. 1 DECEMBER 2022

TO

IS 1528 (PART 7) : 2010 METHODS OF SAMPLING AND PHYSICAL TESTS FOR REFRACTORY MATERIALS

PART 7 METHODS OF SAMPLING AND CRITERIA FOR CONFORMITY

(Second Revision)

(*Page* 5, *clause* **5.2.10**) — Insert the following new clause after **5.2.10**

'**5.2.11** The lot sampled shall be considered as conforming to the requirements of Modulus of Rupture, if the average of all the test results satisfy the requirement and the difference of the individual test results should not vary more than 20 percent (with reference to the highest obtained value). '

(*Page* 5, *clause* **5.2.11**) — Insert the following new clause after **5.2.11**

'**5.2.12** The criteria for conformity of all other test not specified in the clause no. **4.6.2.2** shall be as agreed to between the purchaser and the manufacturer.'

(MTD15)

Publication Unit, BIS, New Delhi, India